

CFT325 - COPPER FOIL TAPE WITH CONDUCTIVE ADHESIVE

PRODUCT DESCRIPTION

3 mil copper foil with an electrically conductive acrylic adhesive and release liner.

PRODUCT CONSTRUCTION

Substrate - 3 mil copper foil comprised of 110 soft anneal copper foil per ASTM B152.

Adhesive - 3M electrically conductive acrylic adhesive.

TECHNICAL DATA	VALUES	TEST METHOD
Adhesive Thickness (mils)	2.0 +/- 0.5	VTP-1 or EQ
Copper Foil Thickness (mils)	3 +/- 0.3	ASTM D1000 or EQ
Width Tolerance (inches)	+/- 0.03	ASTM D1000 or EQ
Peel Strength (oz./inch) Min.-24 hr. dwell	25	ASTM D1000 or EQ
Resistance Through Tape Thickness (milliohms/sq in) max.	30	MIL-STD-202 Method 303 or EQ
Volume Resistance (ohm-cm) max.	6.0	VTP-13 or EQ

* Copper foil may discolor.

*Note: The above are typical values and should **not** be used in writing specifications. The determination of the suitability of this product for any specific use is solely the responsibility of the user. No representations, guarantees or warranties of any kind are made to the accuracy or suitability for specific applications.*



**Delaware Valley
Packaging Group**

1425 WELLS DRIVE BENSLEM, PA 19020
STEVE CONWAY (267) 229-2379